

88-1008B

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re application of:

Shaotian Wang : Group Art Unit: 1755

Serial No.: Unknown : Examiner: J. Pasterczyk

Filed: Herewith :

For: PROCESS FOR THE IN-SITU PREPARATION OF SINGLE-SITE TRANSITION  
METAL CATALYSTS AND POLYMERIZATION PROCESS

Assistant Commissioner for Patents  
Washington, D.C. 20231

PRELIMINARY AMENDMENT UNDER 37 C.F.R. § 1.121

Dear Sir:

Please amend this patent application as follows:

IN THE SPECIFICATION:

Under the title, please add:

-- This is a division of Appl. Ser. No. 09/318,009, filed May 25, 1999. --

IN THE CLAIMS:

Please cancel claims 1-35.

Please enter new claims 36-57 as follows:

-- **36.** A process for the in-situ preparation of a single-site transition metal olefin  
polymerization catalyst which comprises:

(a) forming a precatalyst by contacting a boron-containing ionizing agent with  
a neutral transition metal complex having the formula:




Group 2, 12, or 13 metal compound containing at least 1 alkyl group having from 1 to 8 carbon atoms.---

-- **44.** The process of Claim **43** wherein the organometallic alkylating agent is selected from the group consisting of dialkyl zincs, dialkyl magnesiums, alkyl magnesium halides, alkyl aluminum dihalides, dialkyl aluminum halides, and trialkyl aluminums.---

-- **45.** A process for the in-situ preparation of a supported single-site transition metal olefin polymerization catalyst which comprises:

(a) combining (1) a neutral transition metal complex having the formula:



wherein M is a Group 3-10 metal, L is a bulky ancillary anionic polymerization-stable carbocyclic, heterocyclic or constraint-inducing ligand, X is selected from the group consisting of halogen, C<sub>1-20</sub> alkoxy, C<sub>6-20</sub> aryloxy or alkyl- or aryl-substituted amido, n is 1 to 4, m is 1 to 4 and n+m is equal to the valence of the metal; (2) a boron-containing ionizing agent; (3) a support material; and (4) an inert hydrocarbon;

(b) removing all or a portion of the inert hydrocarbon to obtain a supported transition metal precatalyst; and

(c) introducing the supported transition metal precatalyst into a polymerization system and contacting the supported precatalyst with an organometallic alkylating agent to form a supported cationic transition metal catalyst, wherein the supported precatalyst and organometallic alkylating agent are contacted in the presence of one or more C<sub>2-12</sub> α-olefin monomers.---

-- **46.** The process of Claim **45** wherein the contact of the supported precatalyst and organometallic alkylating agent is carried out under polymerization conditions.---

-- **47.** The process of Claim **45** wherein the support material is an inorganic oxide, inorganic silicate, inorganic chloride, or organic polymer resin.---

-- **48.** The process of Claim **47** wherein the support material is an inorganic oxide selected from the group consisting of silica, alumina, silica-alumina, magnesia, titania, and zirconia.---

-- **49.** The process of Claim **48** wherein the inorganic oxide support is pretreated to remove all or a portion of the hydroxyl functionality present on the surface of the support.---

-- **50.** The process of Claim **49** wherein the pretreatment is accomplished by thermal, chemical, or a combination of thermal and chemical means.---

-- **51.** The process of Claim **50** wherein the thermal pretreatment is carried out by heating at 150°C to 800°C.---

-- **52.** The process of Claim **50** wherein the chemical pretreatment is carried out by contacting the inorganic oxide support with a modifier selected from the group consisting of alumoxanes, alkyl aluminums, alkyl aluminum halides, alkyl aluminum hydrides, alkylsilyl halides, alkylidisilazanes, alkyl and aryl alkoxysilanes, and alkyl, aryl, and alkoxy boron compounds.---

-- **53.** The process of Claim **50** wherein substantially all surface hydroxyl functional groups are removed.---

-- **54.** The process of Claim **45** wherein the boron-containing ionizing agent is a trialkyl borane, triaryl borane or ionic organoborate compound.---

-- **55.** The process of Claim **45** wherein M is a Group 4-6 transition metal.---

-- **56.** The process of Claim **45** wherein the organometallic alkylating agent is a Group 2, 12, or 13 metal compound containing at least 1 alkyl group having from 1 to 8 carbon atoms.---

-- **57.** The process of Claim **56** wherein the organometallic alkylating agent is selected from the group consisting of dialkyl zincs, dialkyl magnesiums, alkyl magnesium halides, alkyl aluminum dihalides, dialkyl aluminum halides, and trialkyl aluminums.---

09/09/2010 10:00:00

REMARKS

This application is a division of Application Serial No. 09/318,009, filed May 25, 1999, and is being filed under 37 C.F.R. 1.53(b). Claims 1-35 from the original application are cancelled in this response. After the amendment is entered, claims 36-57 will remain for consideration. Support for the new claims appears in the specification. The new claims include claims that were divided out of the parent case (now including claim language describing the catalyst), plus additional dependent claims that appeared in the parent case.

Applicant includes with this response, for the Examiner's convenience, copies of the Information Disclosure Statement and the Examiner's Notice of References cited from the parent case. Copies of the references are not included, but Applicant will gladly supply them at the Examiner's request. Applicant respectfully asks the Examiner to consider the cited references.

Respectfully submitted,  
Shaotian Wang

By: Kevin M. Carroll  
Kevin M. Carroll  
Reg. No. 44,596  
Agent for Applicant  
Lyondell Chemical Company  
3801 West Chester Pike  
Newtown Square, PA 19073  
Phone: (610) 359-3480  
August 2, 2001

CUSTOMER NUMBER 24114

09/318,009